

## GTX 190 BACKLIGHT

|                        |                             |
|------------------------|-----------------------------|
| <b>Product</b>         | Digital printing media      |
| <b>Description</b>     | Textile backlight 190gr/sqm |
| <b>Height standard</b> | 1060/1600/3200 mm           |
| <b>Width standard</b>  | 50 m                        |

| Description                 | Unit of measurement | Data                                  | Test method              |
|-----------------------------|---------------------|---------------------------------------|--------------------------|
| <b>Fabric</b>               |                     | yes                                   | DIN EN ISO2060           |
| <b>Construction</b>         | inch                | Pvc+textile                           | DIN60001                 |
| <b>Total weight</b>         | g/sq.m              | 190                                   | DIN53352 BS3424 method5A |
| <b>Weight of textile</b>    | g/sq.m              | 76                                    | DIN53352 BS3424 method5B |
| <b>Weight of pvc</b>        | g/sq.m              | 114                                   | DIN53352 BS3424 method5B |
| <b>Tensile strength</b>     | N/5cm               | Warp: 750<br>Warp: 630                | DIN53354 BS3424 method6A |
| <b>Tearing strenght</b>     | N                   | Warp:48<br>Warp: 40                   | DIN53356 BS3424 method7A |
| <b>Adhesion</b>             | N/5cm               | 60                                    | DIN53357 BS3425 method9B |
| <b>Suitable temperature</b> | C                   | -30/+50                               | DIN53372 BS3424 method10 |
| <b>Flame retardancy</b>     |                     | Upon requested-<br>FR/B1 possible     |                          |
| <b>Printer type</b>         |                     | Solvent/eco-solvent/uv<br>printin etc |                          |